



MG500026

Linear Low Density Polyethylene for Compounding

Product Description

MG500026 is Linear Low Density Polyethylene grade with narrow molecular weight distribution suitable mainly for compounding applications. It is in the powder form has been designed to give excellent flow properties with better low temperature toughness, stress crack resistance and gloss.

Typical Applications

MG500026 is recommended for carpet backing, metal coating and compounding for masterbatch production.

Typical data

Properties	Unit	Value ⁽¹⁾	ASTM Method
Resin Properties			
Melt Flow Rate @ 190°C & 2.16 kg load	g/10 min.	50	D 1238
Density @ 23°C	kg/m ³	926	D 1505
Mechanical Properties⁽²⁾			
1% Secant Modulus	MPa	240	D 638
Tensile Strength @ Yield	MPa	10	D 638
Tensile Strength @ Break	MPa	8	D 638
Tensile Elongation @ Break	%	>350	D638
Flexural Strength	MPa	8	D 790
Flexural Modulus	MPa	200	D 790
Izod Impact	J/m	500	D 256
Hardness (Shore D)	-	50	D 2240
ESCR (100% Igepal), F ₅₀ ⁽³⁾	Hrs	6	D 1693B
ESCR (10% Igepal), F ₅₀ ⁽³⁾	Hrs	3	
Thermal Properties			
Vicat Softening Point	°C	88	D 1525
Brittleness Temperature	°C	< -75	D 746

(1) Typical values; not to be construed as specification limits.

(2) Based on Injection molded specimens

(3) Based on Compression molded sheet

Processing Conditions

Typical processing conditions for MG500026 are:

Barrel temperature: 180 - 230°C (354 - 444°F)

Mold temperature: 15 - 60°C (60 -140°F)

Injection pressure: 600 - 1000 Bar (8700 - 14500 psi)

Food Regulation

MG500026 is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

Storage and Handling

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia
Tel: 966 1 2258000
Fax: 966 1 2259000

Technical Marketing
Tel: 966 1 2659166
Fax: 966 1 2653544
Toll-free 800 1245577

PE Sales:
Fax: 966 1 2258760
Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.